

Abstract of the Disclosure

An oxygen absorber includes an iron powder, and a first layer coated on a surface of the iron powder and formed of iron chloride through a chemical reaction. Further, the oxygen
5 absorber includes a matrix material filled with the iron powder covered with the first layer of iron chloride. It is possible to coat the first layer on the surface of the iron powder with a second layer to obtain more uniform coating.